



STAINLESS STEEL MEDIUM PRESSURE



PROPERTIES

INNERCORE MEDIUM WALL SMOOTHBORE
PTFE TUBE

REINFORCEMENT HIGH TENSILE 304 SS BRAID

JACKETS/COVERS PVC, HYTREL, SANTOPRENE,
SILICONE, POLYESTER BRAID

APPLICATION FOOD & BEVERAGE, CHEMICAL,
INDUSTRIAL

COMPLIANCE MEETS OR EXCEEDS SAE 100R14

SPECIFICATIONS

PART NUMBER	CONDUCTIVE P/N	HOSE SIZE	I.D. NOMINAL	O.D. NOMINAL	MAX WORKING PRESSURE	MIN. BURST PRESSURE	MIN. BEND RADIUS	WEIGHT
			(in.)	(in.)	(psi)	(psi)	(in.)	(lb/ft)
SSMP-03	SSMPC-03	3/16	0.125	0.250	3,000	12,000	2	0.047
SSMP-04	SSMPC-04	1/4	0.187	0.312	3,000	12,000	2	0.077
SSMP-05	SSMPC-05	5/16	0.250	0.375	3,000	12,000	3	0.098
SSMP-06	SSMPC-06	3/8	0.312	0.445	2,500	10,000	4	0.110
SSMP-07	SSMPC-07	7/16	0.375	0.503	2,250	9,000	4.5	0.124
SSMP-08	SSMPC-08	1/2	0.405	0.549	2,000	8,000	5.2	0.124
SSMP-10	SSMPC-10	5/8	0.500	0.648	1,500	6,000	6.5	0.154
SSMP-12	SSMPC-12	3/4	0.625	0.778	1,200	4,800	7.7	0.170
SSMP-14	SSMPC-14	7/8	0.750	0.885	1,100	4,400	8.2	0.198
SSMP-16	SSMPC-16	1	0.875	1.030	1,000	4,000	9	0.273
SSMP-18	SSMPC-18	1 1/8	1.000	1.135	900	3,600	10	0.305
SSMP-20	SSMPC-20	1 1/4	1.125	1.290	750	3,000	16	0.350

Temperature Range: -100°F to 500°F intermittent. -76 °F to 450 °F continuous



ALL HOSE INC
341 SHAKER ROAD, EAST LONGMEADOW MA01028
413-224-2102 • FAX: 413-224-2105 • SALES@ALLHOSE-INC.COM
ALLHOSE-INC.COM





SSMP

STAINLESS STEEL MEDIUM PRESSURE